

Quality 430F
According to Standard ASTM A 582/A 582M - 06
Number -



Comparable Standards EN W.N. BS

1.4105

Chemical Analysis	C %	Mn %	Si %	P%	Cr %	Ni %
	0.12	1.25	1.00	0.06	16.0 to 18.0	-
	Mo %	S%				
	-	0.15 min.				

Hot Work and Heat Treatment

Type	Condition A (Annealed)	Condition T (Intermediate Temper)	Condition H (Hard Temper)
430F	A	-	-

Mechanical Properties at Room Temperature

Types	Condition	Hardness^A (HB)
430F	A	262 max